



ASTM C-170 Compressive Strength of Dimension Stone

Project: Aguado Stone Inc. Project Location: Georgetown, Texas Report #: 25-0404-102 Report Date: 4/4/2025				Project Name: AGUADO STONE GRAY BUFF LUEDERS FAMILY Client #: AGUDSTN Sampled By: Charles Craig Sample Date: 3/31/2025			
Core #	Location	Width	Depth	Ratio 0.9-1.1/1	Load	Area	PSI
Aguado Stone's Buff Gray Lueder							
1	Sample Stone	4.00	4.01	1.00	143050	16.04	8918
2	Sample Stone	4.00	4.01	1.00	150710	16.04	9396
3	Sample Stone	4.04	4.01	1.01	153940	16.20	9502
4	Sample Stone	4.00	4.02	1.00	152210	16.08	9466
5	Sample Stone	4.01	4.00	1.00	162610	16.04	10138
Average							9484
ASTM C-97 Absorption							
2.7%							

Remarks: Tested Dry, Perpendicular to Rift

Respectfully,

Chris Taylor S.E.T.
ETTL Engineers and Consultants, Inc F-3208

This report applies only to the standards or procedures indicated and to the samples tested and/or observed and are not necessarily indicative of the qualities of apparently or similar products or procedures, nor do they represent an ongoing quality assurance program unless so noted. These reports are for the use of the addressed client and are not to be reproduced without written permission.

Tyler, TX

Arlington, TX

Austin, TX

Texarkana, AR

WWW.ETTLINC.COM